

TECHNICAL DATA SHEET



WET WOOD DECKING STAIN

A water based translucent microporous coating offering the ultimate defence for outdoor decking, alongside the unique attribute of being specifically formulated to be applied to wet and dry wood. No need to wait for wood to dry out after jet washing your decking, or the unpredictable British weather. Sadolin Wet Wood Decking Stain has lasting protection to ensure your decking looks great all year round. The formulation contains a biocide to protect against mould and algae growth and advanced UV technology for a durable finish.

AVAILABILITY	
Colour range	Refer to current Sadolin Literature.
Packaging	2.5L
PROPERTIES	
Suitable Surfaces	Decking
Drying time @20°C/65% RH	Touch dry 2-4 hours. Recoat 4-6 hours. Note: Drying times are dependent upon absorption, type of substrate and drying conditions. At low temperatures and/or conditions of high relative humidity, or if wood was wet at the time of application, drying times will be extended.
Finish	Satin Note: On less absorbent/dense timber a higher sheen may be apparent.
Composition	Binder: Acrylic resin Thinner: Water.
Spreading rate	Up to 10m ² per litre on smooth planed timber These figures are intended as a guide. The actual coverage will depend on a number of factors including timber species, surface condition, moisture content, method of application and climatic conditions during application
Wet film thickness	100 micrometres at 10m ² per litre
Dry film thickness	13 micrometres at 10m ² per litre
Volume solids	13%
Flash point	Not applicable
VOC content	EU limit value for this product (cat.A/i): 140 g/l (2010) This product contains max. 30 g/l VOC
Limitations	Do not apply if there is a risk of rain. Do not apply when air or substrate temperatures are likely to fall below 8°C, above 25°C or when the relative humidity is above 80% during application or the drying period. Sadolin Wet Wood Decking Stain is not suitable as a penetrating treatment process. Do not use on substrates previously coated with water repellent preservative treatments unless suitably weathered. The use of linseed oil putty or modified, non setting compounds are not recommended with our Sadolin products. Sadolin Wet Wood Decking Stain is supplied ready to use and should not be thinned.
PREPARATION	
General Timber Advice	Timber surfaces must be suitably prepared, clean and sound. Wash surfaces with water and a mild detergent and rinse with clean water. Remove any green algal growth using a



P O Box 37, Crown House, Hollins Road, Darwen, Lancashire, BB3 0BG. Tel: 01254 704951

Crown Paints Ireland Ltd, Unit 8A, Coolmine Central, Porters Road, Coolmine Ind Est, Dublin 15, D15 AX9A. Tel: 00353 1 8164400

TECHNICAL DATA SHEET



	<p>fungicidal wash. Remove any pools of water after cleaning or rain. Whilst this product can be applied to wet wood do not apply in rain or showery weather. Lightly sand if necessary or scrub with a non-metallic brush in the direction of the grain to remove any loose particles. If excessive weathering has taken place, any grey denatured timber should be sanded back to a clean sound surface. Resinous deposits should be removed with a scraper. Remove any remaining residues and degrease by wiping with a clean, lint free cloth dampened with methylated spirits, frequently changing the face of the cloth. Allow the solvent to fully evaporate before overcoating. Abrade sound timber surfaces in the direction of the grain using medium/medium fine grade (P180/P240) pads/abrasive paper (nothing metallic), taking care not to damage or scratch across surfaces. Remove dust and deposits. "Knotting agents" should not be used with Sadolin systems. Use Sadolin Woodfillers to make good any minor surface defects. General or all-purpose fillers are not suitable. We recommend the use of non-ferrous screws, nails and fixings. Exposed ferrous items may corrode and break the coating film over time if not suitably primed/treated prior to decorating</p> <p>Note: Decking may be slippery when wet, and care should be taken.</p>
New Timber Decking	<p>All surfaces must be sound and free from anything that will interfere with the adhesion of the materials to be applied. Coat any non-treated wood or freshly sawn ends of decking boards with two liberal coats of Sadolin Quick Dry Wood Preserver (when timber is dry). Timber in ground contact (e.g. support posts) should also be preservative treated. Allow 24 hours before overcoating. Remove any surface salts left after preservative treatment with clean water and allow to dry. Remove any pools of water after cleaning or rain. Whilst this product can be applied to wet wood do not apply in rain or showery weather. Where possible, the basecoat, Sadolin Wet Wood Decking Stain, should be applied, all round, prior to fixing.</p>
Previously Coated Decking	<p>Sadolin Wet Wood Decking Stain not suitable for use on surfaces previously coated with a higher build finish, such as varnish or paint. These coatings should be removed completely and timber treated as new timber.</p> <p>On decking previously treated with creosote or similar water repellent treatments ensure they are well weathered and do not retain any smelly/oily surface. This can be tested by splashing with water, if the water is absorbed treatment with Sadolin Wet Wood Decking Stain should be satisfactory.</p> <p>All surfaces must be sound and free from anything that will interfere with the adhesion of the materials to be applied. Remove all defective coatings. Lightly abrade in the direction of the grain, taking care not to break the surface coating. Remove dust. Grey denatured timber should be thoroughly sanded back to clean, bright timber and treated as new. Remove any pools of water after cleaning or rain. Whilst this product can be applied to wet wood do not apply in rain or showery weather. Organic growths should be treated with a suitable fungicidal wash and removed. Bare timber should be patched primed with Sadolin Wet Wood Decking Stain. Remaining sound surfaces should be cleaned with a warm water and mild detergent then rinse thoroughly with clean water.</p>
Colour guidance	<p>The final colour and sheen of translucent coatings are dependent on timber species, colour, cut and presence of existing coating amongst other factors. We recommend a trial application in an inconspicuous area prior to commencement of work to check for colour accuracy. Always intermix (box) packs for colour consistency. Crown Paints is not liable for decorating costs caused as a result of an incorrect colour being applied.</p>
COATING SYSTEM	Apply 3 coats.



P O Box 37, Crown House, Hollins Road, Darwen, Lancashire, BB3 0BG. Tel: 01254 704951

Crown Paints Ireland Ltd, Unit 8A, Coolmine Central, Porters Road, Coolmine Ind Est, Dublin 15, D15 AX9A. Tel: 00353 1 8164400

TECHNICAL DATA SHEET



	With certain substrates profiles and colours, it may be necessary to apply additional coats to achieve required colour
APPLICATION	Stir well before and during use. Use a good quality synthetic bristle brush. Any standing water should be removed with a stiff bristle brush before commencing application. Apply in a full flowing coat, ensuring all surfaces are coated. Ensure end grains and sawn timbers are coated to saturation, after 5-10 minutes redistribute the coating brushing in the direction of the grain. Avoid overspreading.
CLEANING	Return surplus material to container. Wash tools and equipment with warm, soapy water and rinse immediately after use.
MAINTENANCE INFORMATION	Maintenance requirement is indicated by lightening of colour, reduction in sheen or loss of water repellence. Between maintenance redecoration, surfaces may be washed with a warm water and liquid detergent solution to remove surface dirt, rinse off with clean water and allow to dry. We recommend you assess your decking boards annually and recoat as necessary, especially where high levels of weathering or abrasion occurs.
HEALTH AND SAFETY	Please refer to the Safety, Health and Environmental Information on the container. Take special precautions during the surface preparation of pre 1960's painted surfaces as they may contain harmful lead. When preparing the surfaces avoid the inhalation of dust and/or metal particles. Wear a suitable facemask. Material Safety Data Sheets for this and all other Sadolin products are freely available from the place of purchase or the address below, or visit sadolin.co.uk Do not empty into drains, watercourses or access routes to septic tanks.
STORAGE	Store upright and secure. Store in secure dry conditions inaccessible to children or animals. Containers should be kept closed during storage. Do not store below 5°C or above 40°C.
GENERAL INFORMATION	Apply all products in accordance with: BS EN 927-1: Coating materials and coating systems for exterior wood. Classification and selection. BS 6150: Painting of buildings. Code of practice. BS 8000-12: Workmanship on construction sites. Code of practice for decorative wallcoverings and painting BS 8000-7: Workmanship on construction sites. Code of practice for glazing BS EN 335: Durability of wood and wood based products. Use classes: definitions, application to solid wood and wood based products. BS EN 350: Durability of wood and wood based products. Testing and classification of the durability to biological agents of wood and wood-based materials. Every care is taken to ensure that all information provided on this Technical Data Sheet is accurate. Crown Paints is unable to guarantee results as it has no control over the conditions under which its products are applied. Before using this product, please ensure you have the latest information. For help or more information contact the Sadolin Customer Relations Team on: Tel: 0330 024 0298 e-mail: info@sadolin.co.uk website: www.sadolin.co.uk This information is correct at date of issue April 2022



P O Box 37, Crown House, Hollins Road, Darwen, Lancashire, BB3 0BG. Tel: 01254 704951

Crown Paints Ireland Ltd, Unit 8A, Coolmine Central, Porters Road, Coolmine Ind Est, Dublin 15, D15 AX9A. Tel: 00353 1 8164400